

PRODUCT DATA

3^{03 01 00}Maintenance of
Concrete

10-61 RAPID MORTAR

Rapid-setting cement-based mortar
with extended working time

Description

10-61 Rapid Mortar is a one-component shrinkage-compensated cement-based mortar with an extended working time. It is designed for repairing horizontal concrete surfaces.

Yield

0.43 ft³ (0.012 m³) per 50 lb (22.7 kg) bag

When extended 50%:

0.57 ft³ (0.016 m³)

When extended 100%:

0.77 ft³ (0.022 m³)

Packaging

50 lb (22.7 kg) bags

Shelf life 1 year when properly stored

2,500 lb (1,134 kg) bulk bags

Shelf life 6 months when properly stored

Storage

Store and transport in unopened containers at 60 to 80° F (16 to 27° C) in clean, dry conditions.

Features

- Extended working time
- Excellent resistance to freeze/thaw
- Nongypsum based
- Shrinkage compensated
- Can be extended up to 100% by weight with 3/8" (10 mm) aggregate
- Proprietary cement blend

Benefits

- Can be used for deep or large repairs; allows repairs at elevated temperatures
- Outstanding durability
- Volume stability
- Minimizes cracking from drying shrinkage; reduces stress at the bondline
- Economical applications
- Bonds to carbonated and noncarbonated concrete substrates

Where to Use

APPLICATION

- Both small and large-scale repairs
- Structural concrete repairs
- Repairing industrial floors
- Bridges
- Parking decks
- Airport runways

LOCATION

- Horizontal surfaces
- Interior or exterior

SUBSTRATE

- Concrete

How to Apply

Surface Preparation

CONCRETE

1. Concrete must be structurally sound and fully cured (28 days).
2. Saw cut the perimeter of the area being patched into a square with a minimum depth of 1/2" (13 mm).
3. Remove all unsound concrete and roughen the surface to a minimum 1/4" (6 mm) profile amplitude.
4. Remove all laitance, oil, grease, curing compounds, and other contaminants that could prevent adequate bond.
5. The concrete substrate should be saturated surface-dry (SSD), without standing water, before application.

Technical Data

Composition

10-61 Rapid Mortar is a proprietary blend of cement, graded aggregate, shrinkage-compensating agents, and set-control additives.

Compliances

- ASTM C 928

Test Data

The following results were obtained with a water / powder ratio of 5.5 pints (2.6 L) of water to 50 lbs (22.7 kg) of 10-61 Rapid Mortar at 73° F (23° C).

PROPERTY	RESULTS	TEST METHODS
Fresh wet density , lb/ft ³ (kg/m ³)	130 (2,082)	ASTM C 138
Set time , min, at 72° F (22° C)		ASTM C 191
Initial	50	
Final	80	
Working time , min	25	
Length change , % (µstrain)		ASTM C 928
Drying shrinkage	-0.05 (-500)	
Wetting expansion	+0.03 (+300)	
Coefficient of thermal expansion in/in/° F (cm/cm/° C)	6.8 x 10 ⁻⁶ (12.6 x 10 ⁻⁶)	CRD C 39
Modulus of elasticity , psi (GPa)	4.6 x 10 ⁶ (32)	ASTM C 469
Rapid chloride permeability , coulombs	< 300	ASTM C 1202
Freeze-thaw resistance , % RDM, at 300 cycles	100	ASTM C 666
Scaling resistance , at 25 cycles	0 rating; no scaling	ASTM C 672
Slant shear bond strength , psi (MPa)		ASTM C 882, (modified ¹)
1 day	2,300 (16)	
28 days	2,600 (18)	
Splitting tensile strength , psi (MPa)		ASTM C 496
1 day	400 (3)	
28 days	450 (3)	
Flexural strength , psi (MPa)		ASTM C 348
1 day	700 (5)	
28 days	850 (6)	
Compressive strength , psi (MPa), 2" cubes		ASTM C 109
3 hrs	3,000 (21)	
1 day	4,000 (28)	
28 days	8,000 (55)	
Compressive strength , psi (MPa), 3 by 6" cylinders, at 28 days	7,400 (51)	ASTM C 39

¹No bonding agent used; mortar scrubbed into substrate.

All application and performance values are typical for the material, but may vary with test methods, conditions, and configurations.

REINFORCING STEEL

1. Remove all oxidation and scale from the exposed reinforcing steel in accordance with ICRI Technical Guideline No. 03730 "Guide for Surface Preparation for the Repair of Deteriorated Concrete Resulting from Reinforcing Steel Corrosion."
2. For additional protection from future corrosion, coat the prepared reinforcing steel with Zincrich Rebar Primer.

Mixing

1. Add 5-1/2 pints (2.6 L) of clean water to the mixing container for each bag of 10-61 Rapid Mortar. If required, add the correct amount of aggregate to the mixer. Add the powder to the water while continuously mixing with a slow-speed drill and paddle, mortar mixer, or other forced action mixer.
2. Mix for a minimum of 3 minutes until fully homogeneous.

AGGREGATE EXTENSION

1. For repair areas 2 – 4" (51 – 102 mm) in depth, the minimum recommended addition is 15 – 25 lbs (6.8 – 11.4 kg) of 3/8" (10 mm) washed, graded, rounded, SSD, low-absorption, high-density aggregate per 50 lb (22.7 kg) bag.
2. For areas greater than 4" (102 mm) in depth, the minimum recommended addition is 25 – 50 lbs (11.4 – 22.7 kg) of 3/8" (10 mm) washed, graded, rounded, SSD, low-absorption, high-density aggregate per 50 lb bag.
3. The maximum aggregate extension is 50 lbs (22.7 kg) of pea gravel per bag.
4. The performance of 10-61 Rapid Mortar depends on the type, condition, and amount of aggregate added. Rely on trials, testing, and previous experience to determine aggregate suitability.

Application

1. Apply the mixed material onto the prepared saturated surface-dry (SSD) substrate by gloved hand, trowel, or screed. Ensure proper consolidation of the mortar and compaction around reinforcing steel. Minimum application thickness is 1/2" (13 mm).
2. Finish the completed repair, as required, taking care not to overwork the surface.
3. A maximum of 30 minutes should be allowed to mix, place, and finish 10-61 Rapid Mortar at 70° F (21° C).

Clean Up

Clean tools and equipment with clean water immediately after use. Cured material must be removed mechanically.

Curing

Proper curing is extremely important. Cure 10-61 Rapid Mortar immediately after finishing. Use a water-based curing compound that complies with ASTM C 309.

For Best Performance

- Minimum ambient, surface, and material temperature is 50° F (10° C) and rising.
- Do not mix longer than 5 minutes.
- Minimum application thickness is 1/2" (13 mm).
- Consult coating manufacturer for overcoating requirements.
- Make certain the most current versions of product data sheet and MSDS are being used; call Customer Service (1-800-433-9517) to verify the most current version.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

Health and Safety

10-61 RAPID MORTAR

WARNING!

10-61 Rapid Mortar contains silica, crystalline quartz; alumina cement; portland cement; anhydrite ; fly ash; calcium sulfate; silica, amorphous; iron oxide; sulfur trioxide.

Risks

Product is alkaline on contact with water and may cause injury to skin or eyes. Ingestion or inhalation of dust may cause irritation. Contains small amount of free respirable quartz which has been listed as a suspected human carcinogen by NTP and IARC. Repeated or prolonged overexposure to free respirable quartz may cause silicosis or other serious and delayed lung injury.

Precautions

Avoid contact with skin, eyes and clothing. Prevent inhalation of dust. Wash thoroughly after handling. Keep container closed when not in use. DO NOT take internally. Use only with adequate ventilation. Use impervious gloves, eye protection and if the TLV is exceeded or used in a poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable Federal, state and local regulations.

First Aid

In case of eye contact, flush thoroughly with water for at least 15 minutes. In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION. Remove and wash contaminated clothing. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION.

Refer to Material Safety Data Sheet (MSDS) for further information.

Proposition 65

This product contains material listed by the State of California as known to cause cancer, birth defects or other reproductive harm.

VOC Content

0 g/L or 0 lbs/gal less water and exempt solvents.

**For medical emergencies only,
call ChemTrec (1-800-424-9300).**

10-61 RAPID MORTAR

**BASF Corporation
Building Systems**

889 Valley Park Drive
Shakopee, MN, 55379

www.BuildingSystems.BASF.com

Customer Service 800-433-9517
Technical Service 800-243-6739



LIMITED WARRANTY NOTICE Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and BASF shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

For professional use only. Not for sale to or use by the general public.

Form No. 1018980 07/11
Printed on recycled paper including 10% post-consumer fiber.

© 2011 BASF
Printed in U.S.A.