
COATING PROFILE

DESCRIPTION CIM 800 is a tough, weather durable waterproofing membrane specifically formulated to meet the demands of waterproofing above or below grade. This two component, cold, liquid applied urethane adheres to most materials to form a permanent seamless barrier to water. It is especially well suited for roofs over critical spaces (e.g. clean rooms, control rooms), areas with multiple penetrations and curbs, and between-slab waterproofing.

ADVANTAGES CIM 800 is specifically formulated to meet the demands of today's waterproofing market. This tough urethane coating offers exceptional performance.

- Liquid applied and self adhering to most materials used in roofing construction.
- Asphalt extended formula provides superior weatherability with three times the polymer content of modified bitumen membranes.
- Can be applied to complex areas with multiple penetrations and curbs.
- Membrane is tough enough to stand up to normal maintenance traffic.
- Environmentally sound, complying with the toughest VOC standards.
- Accepts aggregate toppings as an integral part of the system for color, texture, traction, and added UV resistance.
- An excellent gutter material.
- Can be repaired when damaged or for penetrations.
- Self flashing.

SURFACE PREPARATIONS

GENERAL: Substrates must be **clean and dry** with no oils, grease or loose debris. CIM Bonding Agent is recommended on all non-porous substrates. Perform adhesion tests to confirm adequacy of surface preparation. See C.I.M. Industries' specific substrate Instruction Guide for specific guidelines.

CONCRETE: ICRI-CSP 4-6 surface profile exposing aggregate. Concrete must exhibit minimum 3,000 psi compressive strength and be free of release agents and curing compounds. The substrate must be clean and dry (less than 5% moisture), and free of contaminates.

STEEL: Minimum 3 mil profile.
Non-Immersion service – SSPC-SP6 / NACE No. 3 Commercial Blast.
Use CIM Bonding Agent for greater adhesion.

OTHER METALS: SSPC-SP1 solvent clean and abrasive blast to roughen and degloss the surface.
Use CIM Bonding Agent for greater adhesion.

GLASS: Thoroughly clean. CIM Bonding Agent must be used for increased adhesion.

WOOD: Substrate must be clean, dry and free of surface contamination.

PREVIOUS COATINGS AND LININGS: CIM 800 may be applied over some existing coatings and linings and achieve acceptable performance. CIM Bonding Agent is recommended for greater adhesion. Finished system results vary due to a variety of project specific factors, including the service conditions to which the system is exposed. Therefore, C.I.M. Industries does not accept responsibility for determining the suitability of an existing coating as a substrate for CIM products. Owner shall perform adhesion tests on any existing coating or lining to determine suitability.

EARTH: Use CIM Scrim.

COLOR CIM 800 is initially shiny black, turning dull over 3 to 6 months when exposed to direct sunlight. For a colored or reflecting surface finish, recoat the CIM 800 and immediately broadcast white or colored aggregate into the coating. See C.I.M Industries' Instruction Guide, "Topcoats" (IG-7) for further instructions.

SOLIDS BY VOLUME 86% (1374 dry mils x sq. ft./gal.)

RECOMMENDED COVERAGE Recommended minimum thickness at all points of the coating is 60 wet mils. Higher coverages may be specified, but extended time is required to insure proper solvent release prior to placing the membrane in service. Contact C.I.M. Industries for additional information.

VOC 111 g/l (0.92 lb./gal.). CIM 800 complies with the toughest VOC regulations.



CIM 800

COMMERCIAL INDUSTRIAL MEMBRANE

TYPICAL PROPERTIES

<p>Abrasion Resistance - Wt. Loss, Taber Abraser CS-17 Wheel, 1000 gr./1000 rev. ASTM D4060</p>	<p>1.2 mg. Loss</p>	<p>Membrane Performance Crack Bridging 10 cycles @ -15°F After heat aging</p>	<p>greater than 1/8" greater than 1/4"</p>
<p>Adhesion to Concrete (dry) Elcometer</p>	<p>350 psi</p>	<p>Membrane Weight</p>	<p>37.8 lbs./100 sq. ft.</p>
<p>Deflection Temperature, (Minimum Use Temperature) ASTM D648</p>	<p>below -40°F</p>	<p>Mix Ratio Weight Volume</p>	<p>9.3:1 11.5:1</p>
<p>Density (Approx.) Premix Activator Mixed & Cured</p>	<p>8.0 lbs./gal. 10.1 lbs./gal. 8.3 lbs./gal.</p>	<p>Mullen Burst Strength ASTM D751, 50 mil</p>	<p>100 psi</p>
<p>Elastomeric Waterproofing ASTM C836 ASTM C957</p>	<p>exceeds all criteria exceeds all criteria</p>	<p>Permeability to Water Vapor ASTM E96 Method E, 100°F, 100 mil sheet</p>	<p>0.03 perms</p>
<p>Electrical Resistivity, Volume ASTM D257, 50% RH, 23°C, 2" disc @ 100 mil thickness</p>	<p>1.0 x 10E14 ohm-cm</p>	<p>Recovery from 100% extension: after 5 minutes after 24 hours</p>	<p>98% 100%</p>
<p>Extension to Break ASTM D412</p>	<p>325%</p>	<p>Service Temperature</p>	<p>-60°F to 180°F</p>
<p>Flammability ASTM D2859 UL790</p>	<p>pass/combustible substrate Class A¹</p>	<p>Softening Point, Ring & Ball ASTM D36 275°F Tear Strength ASTM D624 (Die C)</p>	<p>115 lbs./in.</p>
<p>Hardness, Shore A, min ASTM D2240 @ 77°F</p>	<p>55</p>	<p>Tensile Strength ASTM D412</p>	<p>650 psi</p>

¹Contact C.I.M. Industries for details regarding UL fire ratings

CHEMICAL RESISTANCE

CIM 800 Membrane is resistant to incidental contact from a broad range of acids and alkalis.
Consult C.I.M. Industries for additional information regarding chemical resistance.

All information presented in this publication is believed to be accurate, but it is not to be construed as a guarantee of minimum performance. Test performance results are obtained in a controlled laboratory environment using procedures that may not represent actual operating environments.

**THE INFORMATION PRESENTED IN THIS PUBLICATION IS SUBJECT TO CHANGE WITHOUT NOTICE.
CONTACT C.I.M. INDUSTRIES FOR CURRENT INFORMATION.**

www.cimindustries.com

GENERAL APPLICATION INFORMATION

USE FOR PROFESSIONAL USE ONLY.

- PRECAUTIONS** Avoid contamination with water or moisture. Keep all pails and jugs tightly closed until ready for use. All equipment, air supplies, and application substrates must be **ABSOLUTELY DRY**. Do not apply in wet weather or when rain is imminent or when the CIM 800 or the substrate may become wet within 4 hours after coating. Use caution when applying CIM 800 in confined spaces. See C.I.M. Industries' Instruction Guide, "Applying CIM Within Confined Spaces" (IG-9).
- TEMPERATURE** Surface should be at least 50°F (10°C) and must be 5°F (3°C) above the dew point. **DO NOT APPLY WHEN THE SUBSTRATE OR AMBIENT TEMPERATURE IS RISING OR COATING IS IN DIRECT SUNLIGHT**. CIM 800 should be at least 60°F (15°C) when mixed and applied. CIM 800 may be preheated to facilitate application at low temperatures, but working time will be reduced. See C.I.M. Industries' Instruction Guide "Applying CIM Membranes in Cold Weather" (IG-11).
- EQUIPMENT** Spray equipment requires large diameter hose and air supplied mastic gun. Airless pump may be used to provide fluid side pressure. See "Spray Application of CIM Urethanes" (IG-12) or contact C.I.M. Industries for specific recommendations. Roller, squeegee and trowel may also be used.
- POT LIFE** About 45 minutes. Working time depends on temperature and method of application. Spray application requirements will be significantly shorter.
- PRIMING** Porous substrates such as wood and concrete should be primed with CIM 61 Epoxy Primer to minimize outgassing. The recoat window for CIM 61 Epoxy Primer shall be no longer than 48 hours. See CIM 61 Epoxy Primer coating profile for additional information. Perform adhesion tests to confirm adequacy of adhesion to primer.
- MIXING** **DO NOT THIN. DO NOT HAND MIX.** Begin mixing each pail (4.6 gals.) of CIM 800 Premix using a power mixer (e.g. 1/2" drill and an eight inch mud mixer). Do not draw air into the mix. While mixing, slowly add one jug (0.4 gals.) of CIM 800 Activator to the pail and mix thoroughly for **3 FULL MINUTES**. The proportions are pre-measured; **DO NOT ESTIMATE**. Mixing Jigs and Timers are available from C.I.M. Industries to help eliminate mixing errors and increase productivity on the job. See C.I.M. Industries' Instruction Guide, "Mixing CIM Premix and Activator" (IG-8).
- APPLICATION** Apply CIM 800 directly to a clean and dry substrate. Vertical surfaces will require multiple coats. See C.I.M. Industries' specific Substrate Instruction Guide for explicit guidelines.
- RECOATING** CIM 800 may be recoated in 1 hour and must be recoated soon after the coating no longer comes off on polyethylene (typically within 4 hours of mixing). If the membrane has cured longer than this time, the surface must be severely abraded using surface grinder or other mechanical means, and be free of dust and debris. Use CIM Bonding Agent for better adhesion.
- SPREAD RATE** **Note: Coverages are theoretical and do not account for waste, spillage, irregular surfaces, or application technique. Consult CIM 800 coverage chart for additional coverage information.**
- CURING TIME** Typically, CIM 800 can be placed in service within 24 hours. Contact C.I.M. Industries for specific recommendations.
- CLEAN-UP** Use Mineral Spirits for clean-up of uncured material. Spray equipment must be flushed regularly during application to prevent material from setting up in the hose and pump. Cured material is very difficult to remove. Soaking in solvent will soften the material and may assist in its removal.

CONTACT C.I.M. INDUSTRIES FOR SPECIFIC RECOMMENDATIONS AND INSTRUCTION GUIDES.

www.cimindustries.com



CIM 800

COMMERCIAL INDUSTRIAL MEMBRANE

SHIPPING, STORAGE AND SAFETY DATA

WARNING Flammable. Use only in well ventilated areas. Do not store or use near open flame, sparks or hot surfaces. Keep tightly closed. Avoid contact with moisture or water. Keep out of reach of children.

SAFETY INFORMATION This product contains petroleum asphalt, petroleum distillates, amine compounds and/or other chemical ingredients. Adequate health and safety precautions should be observed during storage, handling, application and curing. Refer to C.I.M. Industries' Material Safety Data Sheets for further details regarding the safe use of this product.

PACKAGING CIM 800 is available in mixed units of approximately 1 gallon and 5 gallons. Each unit consists of a container of premix and a smaller container of activator. Quantities have been premeasured to provide the proper mixing ratio, leaving sufficient room in the premix container to facilitate adequate mixing. **Do not estimate proportions.**

SHIPPING Premix

Activator

Weights

1 gallon kits	7.4 lbs. per can (30 lbs. per box of 4)	1 lb. per bottle (12 lbs. per carton of 12)
5 gallon units	43 lbs. per pail	5 lbs. per jug (40 lbs. per case of 8) (30 lbs. per case of 6)

Properties

Flash Point	101°F	>250°F
Shipping Name	Coating Solution	Not Regulated
DOT Class	Class 3, UN 1139, PG III	Not Regulated

STORAGE

Temperature	20°F to 110°F	70°F to 95°F
Shelf Life	2 years	6 months
NFPA	Class II	Non Flammable

WARRANTY & LIMITATION OF SELLER'S LIABILITY

C.I.M. Industries Inc. (C.I.M.) warrants that for a period of five (5) years from the date of shipment to the initial purchaser the products, when mixed in proper ratios for the proper length of time, (a) will not become brittle or crack and (b) will provide a water barrier. Due to application variables beyond C.I.M.'s control which may affect results, C.I.M. makes no warranty of any kind, expressed or implied, including that of merchantability, other than that the products conform to C.I.M.'s current quality control standards at time of manufacture. If breach of warranty is established the buyer's exclusive remedy shall be repayment of the purchase price of the non-conforming CIM membrane product or, at C.I.M.'s option, resupply of conforming product to replace the non-conforming product. The buyer expressly waives any claim to additional damages, including consequential damages.

THE INFORMATION PRESENTED IN THIS DOCUMENT IS SUBJECT TO CHANGE WITHOUT NOTICE.



CONTACT C.I.M. INDUSTRIES FOR CURRENT INFORMATION.

FOR PROFESSIONAL USE ONLY.

23 Elm St., Peterborough, NH 03458
 Tel: (800) 543-3458 (603) 924-9481
 Fax: (603) 924-9482
 Web site: www.cimindustries.com

www.cimindustries.com