

## **Sure Klean<sup>®</sup> Weather Seal Blok-Guard<sup>®</sup> & Graffiti Control Water Repellent Specification**

*Specifier Note: The information provided below is intended to guide the Architect in developing specifications for products manufactured by PROSOCO, Inc. and should not be viewed as a complete source of information about the product(s). The Architect should always refer to the Product Data Sheet and MSDS for additional recommendations and for safety information. See also PROSOCO Section 07190 Water Repellents.*

*Specifier Note: Paragraph below is for PART 1 GENERAL, Quality Assurance.*

### **Test Area**

Test a minimum 4 ft. by 4 ft. area on each type of masonry. Use the manufacturer's application instructions. Let test area protective treatment cure before inspection. Keep test panels available for comparison throughout the protective treatment project.

*Specifier Note: Paragraphs below are for PART 2 PRODUCTS, Manufacturers and Products.*

**Manufacturer:** PROSOCO, Inc., 3741 Greenway Circle, Lawrence, KS 66046. Phone: (800) 255-4255; Fax: (785) 830-9797. E-mail: [CustomerCare@prosoco.com](mailto:CustomerCare@prosoco.com)

### **Product Description**

Sure Klean<sup>®</sup> Weather Seal Blok-Guard<sup>®</sup> & Graffiti Control is a clear, solvent-based silicone elastomer formulated to weatherproof concrete block and other porous masonry materials and protect treated surfaces from repeated graffiti attacks without altering the natural appearance.

Blok-Guard<sup>®</sup> & Graffiti Control penetrates and fills pores to prevent water penetration through exterior walls exposed to normal weathering. Graffiti removal is fast and easy using Defacer Eraser<sup>®</sup> Graffiti Wipe.

### **Technical Data**

ACTIVE SUBSTANCE: Silicone elastomer

ACTIVE SOLIDS: 9%

FORM: Clear liquid

SPECIFIC GRAVITY: 0.802

FLASH POINT: 100 degrees F (38 degrees C) (ASTM D 3278)

WT.GAL.: 6.67 lbs.

VOC content: 725 g/L

FREEZE POINT: <-22 degrees F (<-30 degrees C)

### **Limitations**

- Not suitable for extremely dense or polished surfaces.
- Not suitable for asphaltic surfaces.
- Not recommended for below-grade applications.
- Will not prevent water penetration through structural cracks, defects or open joints.
- May damage glass or be difficult to remove. Always protect.
- Not recommended for horizontal surfaces

*Specifier Note: Paragraphs below are for PART 3 EXECUTION, Installation.*

### **Application**

Before applying, read "Protect" and "Precautionary Measures" sections in the Manufacturer's Product Data Sheet for Weather Seal Blok-Guard<sup>®</sup> & Graffiti Control. Refer to the Product Data

Sheet for additional information about application of Blok-Guard® & Graffiti Control. Do not dilute or alter.

**Vertical Application Instructions**

For best results, apply Blok-Guard® & Graffiti Control “wet-on-wet” to a visibly dry and absorbent surface.

**Spray:**

1. Saturate, “wet-on-wet” from the bottom up, creating a 6-8” rundown below the spray contact point. Avoid excessive overlapping.
2. Let the first application penetrate the masonry surface for 2 to 3 minutes. For heavily textured and porous surfaces, reapply in same saturating manner to ensure complete coverage of recessed surfaces.
3. Immediately brush out runs and drips to prevent build up.

**Brush or Roller:**

1. Thoroughly saturate the surface. Avoid excessive overlapping.
2. Brush out runs and drip to prevent buildup.

**Fluted architectural block:**

Spray in an “overlapping X pattern” for complete coverage of recessed surfaces.

**Dense, smooth surfaces:**

Apply enough in a single saturating application to completely wet the surface. Avoid excessive overlapping. Back roll all runs and drips for a uniform appearance. One application is normally enough.

**Wood:**

Saturate to the point of rejection. Let first application penetrate 2-3 minutes. Reapply in the same saturating manner. Not appropriate for horizontal surfaces.