

Sure Klean[®] Dicone NC9 Silicone Sealant & Adhesive Remover Specification

Specifier Note: The information provided below is intended to guide the Architect in developing specifications for products manufactured by PROSOCO, Inc. and should not be viewed as a complete source of information about the product(s). The Architect should always refer to the Product Data Sheet and MSDS for additional recommendations and for safety information. See also PROSOCO Section 04900 Masonry Restoration & Cleaning.

Specifier Note: Paragraph below is for PART 1 GENERAL, Quality Assurance.

Test Area

Test a minimum 4 ft. by 4 ft. area on each type of masonry. Use manufacturer's application instructions. Let the test panel dry 3 to 7 days before inspection. Keep test panels available for comparison throughout the cleaning project.

Specifier Note: Paragraphs below are for PART 2 PRODUCTS, Manufacturers and Products.

Manufacturer: PROSOCO, Inc., 3741 Greenway Circle, Lawrence, KS 66046. Phone: (800) 255-4255; Fax: (785) 830-9797. E-mail: CustomerCare@prosoco.com

Product Description

Sure Klean[®] Dicone NC9 is a specially formulated silicone "digestant," that removes silicone-based sealants and adhesives, cured silicone elastomers and silicone water repellent overspray. Dicone NC9 uses new solvent technology to dissolve cured silicone resins and polymers with a nonflammable, nonchlorinated and nonaromatic cleaning solution.

Dicone NC9 is suitable for removing silicone residues from brick, concrete, natural stone, glass, and most metal and painted surfaces and an excellent cleaning solvent for removing cured silicone sealants and adhesives from mixing and application equipment. Equipment parts immersed in Dicone NC9 for 1 to 2 hours are cleaned of all silicone residues. Ideal for cleaning and maintenance of bulk caulking guns, pumps, sprayers and dispensing surfaces. Does not attack ceramic, plastic or most synthetic surfaces.

Technical Data

FORM: Clear brown liquid

FLASH POINT: 185 degrees F (85 degrees C) ASTM D 3278

pH: <1.0 (anhydrous concentrate)

WT./GAL.: 6.85 lbs.

SPECIFIC GRAVITY: 0.823

FREEZE POINT: <-22 degrees F (<-30 degrees C)

Limitations

- Surface and air temperatures should be at least 40 degrees F during application.
- Dicone NC9 is moisture sensitive - contamination by rain, rinse waters or other sources will cause loss in effectiveness.
- Attacks nylon and similar finishes on architectural aluminum and other building surfaces. May stain or discolor sensitive metals.

Specifier Note: Paragraphs below are for PART 3 EXECUTION, Installation.

Application

Before applying, read "Protect" and "Precautionary Measures" sections in the Manufacturer's Product Data Sheet for Dicone NC9. Do not dilute or alter.

Removal of silicone sealant/adhesive residues:

1. Surfaces to be cleaned should be completely dry before application.
2. Apply undiluted Dicone NC9 directly from the container.
3. Let the material stay on the surface 10-20 minutes or until the solution begins to dry.
4. Reapply NC9 to the surface and agitate with a synthetic abrasive pad or brush if necessary.
5. Repeat steps 3 and 4 until sealant/adhesive residue has completely dissolved or broken free from the surface.
6. After all sealant/adhesive has dissolved or broken free, water rinse thoroughly with pressure washer or garden hose making sure to rinse off all residues.

Removal of water repellent overspray:

1. Surfaces to be cleaned should be completely dry before application.
2. Apply concentrate NC9 (do not dilute) liberally to the oversprayed area.
3. Let the material stay on the surface for 5 to 10 minutes or until the solution begins to dry.
4. Reapply NC9 to the surface and agitate with a synthetic abrasive pad or brush.
5. After all residues have dissolved or broken free, thoroughly rinse the surface with fresh water. Glass surfaces should be given a final cleaning with a commercial glass cleaner.