



POLYCOAT PRODUCTS

A Division of American Polymers Corp.

POLYGLAZE 400 FR *Fire Rated Aliphatic Urethane Polyurea Topcoat*

DESCRIPTION

Polyglaze 400 FR is an aliphatic, two component, liquid applied, moisture cured, urethane polyurea coating.

FEATURES

- ❖ Excellent Durability
- ❖ Excellent Weatherability
- ❖ Excellent UV Resistance For Gloss Retention
- ❖ Fire Retardant

TYPICAL USES

- ❖ Concrete
- ❖ Heavy Pedestrian Traffic
- ❖ Some Types of Chemical Spills
- ❖ Plywood
- ❖ Vehicular Traffic

COLORS

Stone Grey, Dolphin Grey, Battleship Grey, Tan, Indian Sand, White

Custom colors are also available. Minimum order of 100 gallons (380 liters). See color chart for special provisions.

PACKAGING

6 gallon kit: One 6 gallon (22.68 liter) pail containing 1 gallon bag of Polyglaze 400 FR Part-1 Powder. One 5 gallon (18.9 liter) pail containing 5 gallons of Polyglaze 400 FR Part-2 Liquid.

MIXING

The volume mixing ratio is 1 part Polyglaze 400 FR Part-1 Powder to 5 parts of Polyglaze 400 FR Part-2 Liquid.

Step 1: Mix the Polyglaze 400 Liquid using a mechanical mixer (Jiffy Mixer) at slow speeds or by hand for at least 5 minutes until a homogeneous mixture and color is obtained. Use caution not to whip too much air into the material as this may result in pinhole blisters or shortened potlife.

Step 2: Remove plastic bag of Polyglaze 400 FR Part-1 Powder from the 6 gallon (22.68 liter) pail and set aside. Fill this empty container half full with the pre-mixed Polyglaze 400 FR Part-2 Liquid. Slowly add Polyglaze 400 FR Part-1 Powder, mixing with mechanical mixer. Ensure that all powder is transferred from the bag to the container. Continue mixing until no lumps are present, again being careful not to entrap air in the mixture.

Step 3: When Polyglaze 400 FR Part-1 Powder has been thoroughly blended into Polyglaze 400 FR Part-2 Liquid add the rest of Polyglaze 400 FR Part-2 Liquid. Mix with mechanical mixer until uniform mixture is obtained. Mixed material must be used within 2-4 hours of mixing the two components.

APPLICATION

For best results, airless sprayer or phenolic resin core roller

TECHNICAL DATA

Coverage Rate, per 100 sq. ft.	1¼ gal. 0.51 l/m ²
Dry Film Thickness per Coat	11 ± 2 dry mils 279 ± 50 micron
Hardness, ASTM D-2240	95 ± 5 Shore A
Specific Gravity	1.36
Total Solids by Weight, ASTM D-2369	79.42%
Total Solids by Volume, ASTM D-2697	67.7%
Viscosity at 75°F (24°C)	2400 ± 500 cps
Volatile Organic Compounds, ASTM D-2369-81	2.33 lb/gal 280 gm/liter

may be used but extra care should be taken not to cause air bubbles.

Apply Polyglaze 400 FR evenly over the entire deck. Application should be continuous to ensure a smooth and level coat with no lines or streaks to disfigure the deck.

CURING

At 70°F (21°C) and 50% relative humidity, allow each coat to cure a minimum of 16 hours between each coat. If more than 48 hours passes between coats, re-prime the surface with Polyprime 21 or 2180 before proceeding.

Allow 24 hours before permitting light pedestrian traffic and at least 72 hours before permitting heavy pedestrian or vehicular traffic on the finished surface.

Uncured Polyglaze 400 FR is very sensitive to heat and moisture. Higher temperatures and/or high humidity will accelerate the cure time. Use caution in batch sizes and thickness of application.

Low temperature and/or low humidity extend the cure time.

EQUIPMENT CLEANUP

Equipment should be cleaned with an environmentally safe solvent, as permitted under local regulations, immediately after use.

STORAGE

Polyglaze 400 FR has a shelf life of six (6) months from date of manufacture in original, factory sealed containers.

LIMITATIONS

Surfaces must be dry, clean and free of foreign matter.

Surface may be slippery when wet.

Containers that have been opened must be used as soon as possible.

Do not dilute under any circumstance.

Mix only materials that can be used within 2-4 hours.

WARNING

This product contains Isocyanates and Solvent.

Please read all information in the general guidelines, product data sheets, guide specifications and material safety data sheets (MSDS) before applying material. Published technical data and instructions are subject to change without notice. Contact your local Polycoat Products representative or visit our website for current technical data and instructions.

LIMITED WARRANTY

Polycoat Products warrants its products to be free of manufacturing defects and that they will meet Polycoat Products current published physical properties. Polycoat Products warrants that its products, when properly installed by a state licensed waterproofing contractor according to Polycoat Products guide specifications and product data sheets over a sound, properly prepared substrate, will not allow water migration for a period of one (1) year. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. There are no other warranties by Polycoat Products of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Polycoat Products shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Polycoat Products shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Polycoat Products reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Polycoat Products makes no claim that these tests or any other tests, accurately represent all environments.