

TREMCO

Vulkem® 911

One-Part High Performance Elastomeric Sealant

S

Product Description:

Vulkem 911 is a one-part, moisture curing, polyurethane sealant. Vulkem 911 offers good performance in moving joints. Vulkem 911 does not require a primer on most construction materials.

Basic Uses:

Vulkem 911 is an excellent sealant for use in moving joints. Typical applications for Vulkem 911 include: expansion and control joints, perimeter caulking (windows, door, panels), reglets, flashing and where immersed conditions are a requirement. Vulkem 911 is capable of +35%/-35% movement when correctly installed into a properly prepared joint.

Limitations:

- Do not apply over damp or contaminated surfaces.
- Use with adequate ventilation.

Packaging:

1/12 gallon (300mL) Cartridges, 20 oz. (600mL) Sausages, 2 (7.57 L) and 5 gallon (19 L) pails and 55 gallon (208 L) drums.

Standard Colors:

Aluminum, Black, Bronze, Buff, Dark Bronze, Gray, Ivory, Limestone, Redwood Tan, and White

APPLICABLE STANDARDS:

Conforms to U.S. Federal Specification TT-S-00230C, Type II, Class A and ASTM C920, Type S Grade NS, Class 35, Use NT, M, A, I and O, CAN/CGSB 19.13-M87.

INSTALLATION

Joint Design & Dimensions

May be used in any vertical or horizontal joint designed in accordance with accepted architectural/engineering practice. Joint width should be 4 times anticipated movement, but not less than 1/4 inch (6.4 mm) wide.

For joints 1/4 inch (6.4mm) to 1/2 inch (12.7mm) wide, the width to depth ratio should be equal. Joints 1/2 inch (12.7mm) wide or greater should have a sealant depth of 1/2 inch (12.7mm). Minimum joint size is 1/4 inch by 1/4 inch (6.4mm by 6.4mm).

Surface Preparation:

For good adhesion, the joint interface must be sound, clean and dry. Depending on the substrates, or presence of form release agents, masonry waterproofings, dust, loose mortar or laitance, architectural

paints or finishes, the joint surface may require a thorough wire brushing, grinding, sandblasting, solvent washing and/or primer.

Tooling & Cleaning:

Tooling is recommended immediately after application to insure firm, intimate contact with the joint interface. Dry tooling is preferred. Excess sealant and smears adjacent to the joint can be removed with Xylol or Toluol before sealant cures.

Joint Backing-Bond Breaking Tape:

Closed cell polyethylene backer rods are preferred as joint backing to control depth of sealant bead. Where depth of joint will prevent use of joint backing, an adhesive backed polyethylene tape should be installed to prevent three-sided adhesion. Joint backing must be dry at time of sealant application.



Application:

Vulkem 911 is easy to apply with conventional caulking equipment. Fill joint completely and tool. At 75°F (23.9°C), 50% R.H. a durable skin forms within 6 hours. Curing continues at the rate of 1/16 inch (1.6mm) depth per day. The cure rate may be slightly reduced at lower temperatures and less humidity.

Maintenance:

Damaged sealant can be repaired. Consult your Tremco Distributor or Representative for repair procedures.

Availability:

Immediately available from your local Tremco Field Representative, Tremco Distributor or Tremco Warehouse.

**Warranty:**

Tremco warrants its Vulkem Sealants to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of

MERCHANTABILITY and FITNESS

FOR A PARTICULAR PURPOSE, with respect to Vulkem Sealants, Tremco's sole obligation shall be, at its option, to replace, or to refund the purchase price of the quantity of Vulkem Sealant proved to be defective and Tremco shall not be liable for any loss or damage.

TYPICAL PHYSICAL PROPERTIES

ASTM C920 TT-S-00230C	Requirement	Vulkem 911 Results
Rheological Properties at 40 and 122°F. (4.4 and 50°C.)	3/16" (4.8mm) Maximum Flow No Deformation	0 None
Extrusion Rate	45 Seconds Maximum	5
Continuous Immersion in Liquids	C1247-98	Passes
Hardness Properties	15-50 (Shore A)	35
Weight Loss	Less than 10%	7
Tack Free Time	Tack Free 72 Hours Maximum	6-8 Hours
Stain & Color Change	No Visible Change No Stain	None None
Durability-Cyclic Movement Adhesion & Cohesion	1-1/2 sq. in. (9.7cm ²) Max Total Bond Loss	Passes
Adhesion-in-Peel	Not less than 5 pli (22N)	Aluminum- 18 pli (80N) Concrete- 20 pli (80N) Brick- 19 pli (85N)
Effects of Accelerated Weathering	Less than 25% Bond Loss No cracks greater than #2 on U.V. and Cold Temperature Bond Test	No Adhesion Loss Passes

For MSDS and Spec Data Sheets,
Call our 24 Hour Fax-Back Line:

1-800-551-2806

or visit our website:

www.tremcosealants.com

TREMCO

Sealant/Weatherproofing Division

3735 Green Road • Beachwood, Ohio • 44122 • Phone: (216) 292-5000 • (800) 321-7906
220 Wicksteed Avenue • Toronto, ON M4H 1G7 • Phone: (416) 421-3300 • (800)363-3213